



date: 01.01.2016

**data sheet**      **product**    **TUBE BUTYLE**

Parameter	Value	Unit	Norm
Elastomer base	IIR		
Geometry	Tube		
Density	1,4	g/cm <sup>3</sup>	ISO 2781
Hardness	60 +/-5	Shore A	ISO 7619-1
Elongation	5	MPa	NF ISO 37
Elongation at break	420	%	NF ISO 37
Temperature	-40 to +80	°C	
Color	white		

**Specification**

./.

Excellent gas permeability, good resistance to aging

**Chemical resistance**

Good resistant to alcohols, aldehydes, glycols, ketones, bases hypochlorides, silicone oils, vegetable oils and fats, as well as water vapor.

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the finals products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.

We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).