CIEP
CRAUSAZ ARES-ARMEMENT - G.J.S.

date: 01.01.2016

data sheet product TUBE SIL CELLULAIRE

Parameter	Value	Unit	Norm
Elastomer base	Silicone foam		
Geometry	Tube		
Density	0,25	g/cm³	ISO 845
Hardness	15 +/-5	Shore A	ASTM D 2240
Tensil strength	1200	kPa	ISO 1798
Elongation at break	200	%	ISO 1798
Compression set	10 at 70 ° C; 22 h	%	ISO 1856
Thermal conductivity	0,07	W/mK	VDE 0304
Temperature	-50 to +200 °C		
Color	reddish-brown		

Specification ./.

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the finals products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.
We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).